

Auracast 405

High performance low viscosity PCE based admixture for high early strength for SCC & flow concrete.

Uses

Auracast 405 is a high performance super plasticizer suitable for precast concrete industry to obtain high early strength and moderate workability retentions are required.

Auracast 405 developed to use in:

- Moderate workability retention concrete.
- Suitable for Self-compacting concrete.
- High performance concrete.
- High early strength.

Standard Compliance

Auracast 405 complies to IS:9103 : 1999 as a water reducing admixture.

Advantages

Low viscosity admixture suitable for precast industry

Suitable for concrete having cement replacements and low water cement ratio

Provides high early strength without increase in cement content or reduction in workability. Ideal for precast concrete production

Reduce rate of workability loss normally associated with super plasticiser. Reduces shrinkage cracking because of lower water cement ratio. Makes the concrete water impermeable

- Better resistance to Carbonation
- Reduce Shrinkage and Creep
- Increased durability

Description

Auracast 405 is a unique combination of new generation super plasticizer based on polycarboxylic ether polymer with long lateral chain. Electrostatic dispersion mechanism considerably reduces the water demand in flowable concrete. It is supplied as a light brown liquid, instantly dispersible in water.

Auracast 405 disperses the cement particles effectively in the concrete mix and hence exposes a larger surface area to the hydration process. This effect is used either to increase the strength or to produce high workability concrete or reduce cement content of concrete or to retard the setting time of concrete.

Technical support

Fosroc provides technical advisory service for on-site assistance and guidance on mix design, optimum dosage evaluation of trials.

Properties

Appearance	: Light Brown Liquid
pH	: Minimum 6.0 *
Volumetric mass @ 25° C	: 1.05 to 1.09 kg / liter *
Chloride Ion content	: As per BS EN : 480-10-1997* (Product contains a chemical which interferes in the procedure as per IS 9103)
Workability Retention	: 2 hours and more Depending on Dosage

* The uniformity parameters like specific gravity, pH, chloride content etc. will vary for specific customer requirements and mix design. Please refer our MTC issued for specific product configuration for measuring our product parameters that will be constantly and consistently administered.

Dosage

The optimum dosage of Auracast 405 to meet specific requirement should always be determined by conducting laboratory and batch trials. However the normal dosage ranges between 0.3 to 2.0 percent by weight of total cement or binder content.

Dosage beyond Limits:

Dosage beyond limits can be used to meet particular mix requirements in consultation with Fosroc technical department

Effects of overdosing

Overdosage may cause delay in the setting time and segregation.

Estimating

Packaging

Auracast 405 is available in 20 and 200 kg drums and bulk tankers.

Auracast 405

Storage

Auracast 405 has a minimum shelf life of 12 months provided the temperature is kept within range of 5°C and 50°C.

Precautions

Health and safety instructions

Auracast 405 does not fall into the hazard classifications of current regulations. However it should not be swallowed or allowed to come in contact with skin or eyes.

Suitable protective gloves and goggles should be worn.

Splash on skin should be cleaned with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately do not induce vomiting.

Fire

Auracast 405 is water based and non- flammable.

Cleaning and disposal

Spillage of Auracast 405 should be absorbed onto sand, earth or vermiculite and transferred to suitable container. Remnants should be hosed down with large quantity of water.

The disposal of excess or waste material should be carried out

in accordance with local legislation under the guidance of the local waste regulatory authority.

Additional information

The Fosroc range of associated products includes high strength cementitious, epoxy grout, polyester resin based mortar for rapid pre-setting of steel shims to level or for direct bedding of small base plates; Resin Anchoring systems for same day anchoring of bolts in drilled holes in concrete or rock. Also available a range of products for use in construction; viz., curing compounds, release agents, flooring systems, repair mortars, sealants and waterproofing materials.

Separate datasheets are available on these products.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: +91 44 61304500

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800
Fax: 022 62296809

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0280