

# Nitomortar S

## High strength, abrasion-resistant, epoxy reinstatement mortar

### Uses

For fast and permanent patch repair of concrete, particularly where high strength, abrasion and chemical resistance is required. It is ideally suited for:

- Sewage tanks
- Sea walls
- Industrial floors
- Use as a bedding mortar
- Joint arris repairs

### Advantages

- High ultimate strength - suitable for structural use.
- Early development of strength minimises disruption.
- Abrasion-resistance: suitable for heavily trafficked areas.
- Highly resistant to a wide range of chemicals.
- Will cure under damp conditions - cured product is highly impermeable to water.
- Pre-weighed components ensure consistency.

### Description

Nitomortar S is a three-component material supplied in pre-weighed quantities ready for on-site mixing and use. It is based on a high quality, solvent-free, epoxy resin system; with special aggregates to provide high strength and excellent abrasion resistance.

### Technical Support

Fosroc offers a comprehensive range of high performance high quality, construction products. In addition to a wide range of quality products, Fosroc offers a technical support package to specifiers and contractors which includes assistance with product selection and technical advice from staff with unrivalled experience in the industry.

### Properties

The following results were obtained at a temperature of 20°C unless otherwise specified.

Test Method	Typical Result	
Compressive Strength (BS 6319 Part 2)	70 N/mm <sup>2</sup> at 7 days	
Flexural Strength (BS 6319 Part 3)	20 N/mm <sup>2</sup> at 7 days	
Tensile Strength (BS 6319 Part 7)	10 N/mm <sup>2</sup> at 7 days	
Water Absorption	0.2% (concrete = 2.0 – 2.5%)	
BRE Impact Resistance (BS 8204 Part 1 : 1987)	Category A	
	20°C	35°C
Pot Life	45 mins	20 mins
Initial Hardness	24 hours	16 hours
Full cure	7 days	4 days
Fresh Wet Density	2000 kg/m <sup>3</sup> (fully compacted)	

Fully cured blocks of Nitomortar S were continually immersed at 20°C in a wide range of aggressive chemicals found in industrial environments. Tests were performed by constant immersion over a set period, followed by visual inspection and testing for Shore D hardness.

### Acids (m/v)

Citric acid 10%	:	Resistant
Tartaric acid 10%	:	Resistant
Hydrochloric acid 25%	:	Resistant
Sulphuric acid 10%	:	Resistant
Phosphoric acid 50%	:	Resistant
Lactic acid 10%	:	Resistant
Nitric acid 10%	:	Resistant

### Alkalis (m/v)

Sodium Hydroxide 50%	:	Resistant
----------------------	---	-----------

### Solvents & organics

Diesel fuel/petrol 100%	:	Resistant
Hydrocarbons 100%	:	Resistant

### Aqueous solutions

Sugar solutions (sat.)	:	Resistant
------------------------	---	-----------

# Nitomortar S

---

Note: All the above results have been determined by laboratory controlled tests and are in excess of those expected in practice. Nevertheless, success in use will be determined by the implementation of good housekeeping practice.

## Design criteria

Nitomortar S can be applied in sections up to 50 mm thickness in horizontal locations, and 12 mm in vertical locations, in a single application and without the use of form work, dependent upon the repair geometry. Nitomortar S can be used for emergency repairs where fast strength gain is important. When properly compacted, the mortar is highly impermeable. In certain instances, Nitomortar S can be used on metal substrates. Contact the local Fosroc office for advice in this respect. For fast repairs in vertical and overhead locations where a higher-build, lightweight formulation is required, the use of Nitomortar HB is recommended.

## Instructions for Use

### Preparation

Clean the surface and remove any dust, unsound material, plaster, oil, paint, grease, corrosion deposits or algae. Roughen the surface and remove any laitence by light scabbling or gritblasting. Saw cut or cut back the extremities of the repair locations to a depth of at least 5 mm to avoid feather-edging and to provide a square edge. Break out the complete repair area to a minimum depth of 5 mm up to the sawn edge. Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off test. Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Grit-blasting is recommended for this process.

### Substrate priming

Horizontal substrates should be primed using Nitoprime 25. Predominantly vertical and metal substrates should be primed using Nitocote Primer Sealer\*. In both cases, the primer should be mixed in the proportions supplied, adding the entire contents of the 'hardener' tin to the 'base' tin. The two components should be thoroughly

mixed together by hand for 3 minutes. The mixed primer should be scrubbed well into the prepared substrate, taking care that all imperfections in the surface are properly coated and avoiding 'ponding' in depressions. If the primer is absorbed within 30 minutes, a second coat should be applied before continuing.

Nitomortar S can be applied as soon as the primer has started to gel but still has surface 'tack'. This is normally between 30 minutes and 4 hours dependent on the ambient and substrate temperatures. If the primer cures hard, a second application must be made before application of Nitomortar S. The usable life of the mixed primer is approximately 60 minutes at 20°C or 30 minutes at 35°C.

### Mixing

Care should be taken to ensure that Nitomortar S is thoroughly mixed to produce a fully homogeneous, trowellable mortar. Nitomortar S must be mixed mechanically. The 'hardener' and 'base' components should be stirred thoroughly in order to disperse any settlement before mixing them together. The entire contents of the 'hardener' container should then be emptied into the 'base' container and manually mixed for 3 minutes, then emptied into a forced action mixer of adequate capacity (e.g. Cretangle or Pennine). Add the aggregate slowly with the mixer running and continue for 2 to 3 minutes until all the components are thoroughly blended. Under no circumstances should part packs be used.

### Application

Apply the mixed Nitomortar S to the prepared substrate by wood float, pressing firmly into place to ensure positive adhesion and full compaction. Thoroughly compact the mortar around any exposed reinforcement. In restricted location, or where exposed reinforcing steel is present, application by gloved hands is an acceptable alternative but, in all cases, the product must be finished to a tight surface with a steel trowel. Nitomortar S can be applied in sections up to 50 mm thickness in horizontal locations or up to 12 mm thickness in vertical locations in a single application and without the use of form work. Thicker vertical sections may sometimes be possible dependent on the profile of the substrate and the volume of exposed reinforcing steel but should generally be built up in layers.

# Nitomortar S

When larger areas are being rendered, a chequer board application technique is recommended. Note: the minimum applied thickness of Nitomortar S is 5 mm.

## Build-up

Additional build-up can be achieved by application of multiple layers. Exposed steel reinforcing bars should be firmly secured to avoid movement during the application process as this will affect mortar compaction, build and bond. Where thicker sections are required, the surface of the intermediate applications should be scratch-keyed to provide a suitable surface for subsequent layers.

The application of additional layers should follow between 8 and 24 hours (@ 20°C) after the first application. This time should be reduced at higher temperatures. Re-priming and a further application of Nitomortar S may then proceed. If sagging occurs during application, the Nitomortar S should be completely removed and reapplied at a reduced thickness on to the correctly re-primed substrate.

## Finishing

Nitomortar S is finished by the use of a wood float and closed with a steel trowel. The completed surface should not be overworked.

## High temperature working

At ambient temperatures above 35°C, Nitoprime 25, Nitocote Primer Sealer and Nitomortar S will have shorter pot lives and open working time. The materials should be stored in the shade or in an air-conditioned environment and should not be applied in direct sunlight.

## Curing

Curing protection is not necessary for Nitomortar S.

## Cleaning

Nitoprime 25, Nitocote Primer Sealer and Nitomortar S should be removed from tools, equipment and mixers with Fosroc Solvent 102 immediately after use.

## Estimating

### Supply

Nitomortar S	:	8 litre packs
Nitoprime 25	:	1 and 4 litre packs
Nitocote Primer Sealer	:	1 and 4 litre packs

Fosroc Solvent 102	:	5 litre cans
--------------------	---	--------------

### Coverage

Nitoprime 25	:	4.0 - 5.0 m <sup>2</sup> /litre
Nitocote Primer Sealer	:	4.0 - 5.0 m <sup>2</sup> /litre

Note : The coverage figures for Nitoprime 25 and Nitocote Primer Sealer are theoretical - due to wastage factors and the variety and nature of possible substrates, practical figures will be reduced.

## Storage

### Shelf life

All products have a shelf life of 12 months at 20°C if kept in a dry store in the original, unopened bags or packs.

### Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperatures, the shelf life may be reduced to 4 to 6 months.

## Limitations

Do not mix part packs under any circumstances. Nitomortar S should not be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour. If any doubts arise concerning temperature or substrate conditions, consult the local Fosroc office. The material should not be applied at less than 5 mm thickness. Greater thicknesses than those specified above can be achieved by the application of subsequent layers. Larger areas should be applied in a 'chequer board' fashion. For higher build characteristics to vertical locations, or for overhead application, Nitomortar HB is recommended.

## Precautions

### Health and safety

Nitoprime 25, Nitocote Primer Sealer, Nitomortar S and Fosroc Solvent 102 should not come in contact with skin or eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye protection. If working in confined areas, suitable respiratory protective equipment must be used.



# Nitomortar S

The use of barrier creams provides additional skin protection. In case of contact with skin, remove immediately with resin removing cream followed by washing with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.

## Fire

Nitomortar S and Nitocote Primer Sealer are non-flammable. Nitoprime 25 and Fosroc Solvent 102 are flammable. Keep away from sources of ignition. No smoking. In the event of fire, extinguish with CO<sub>2</sub> or foam. Do not use a water jet.

## Flash points

Nitoprime 25	:	39°C
Fosroc Solvent 102	:	33°C

For further information, refer to the Product Material Safety Data Sheet.

## Additional Information

### Overcoating with protective/decorative finishes

Nitomortar S is extremely durable and resistant to a wide range of acids, alkalis and industrial chemicals and will provide excellent protection to the concrete and embedded steel reinforcement within the repaired location. The surrounding parts of the structure may benefit from the application of a protective coating, thus bringing them up to the same protective standard as the repair itself. Fosroc recommends use of the Nitocote range of epoxy resin, chemical-resistant, protective coatings.

For surrounding areas not subjected to chemical attack or physical wear, Fosroc recommend the use of the Dekguard range of anti-carbonation, anti-chloride protective coatings. These products provide a decorative and uniform appearance as well as protecting areas of the structure which might otherwise be at risk from the environment. Nitocote epoxy resin protective coatings should be applied within 24 hours. Dekguard products should not be applied until the Nitomortar S is at least 3 days old.

For further advice, consult the local Fosroc office.



## Fosroc Sdn. Bhd.

No 8 Jalan Trompet, 33/8  
Seksyen 33, 40400 Shah Alam  
Selangor, Malaysia.

### Branch Office:

29, Jalan Zainal Abidin,  
10400 Penang, Malaysia.

[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

**telephone:**  
+60 3 5191 5660

**fax:**  
+60 3 5191 6960

**email:**  
enquiry@malaysia.fosroc.com

+60 4 2287 464

+60 4 2292 661

