

# Fosroc® Nitoseal® SC600



constructive solutions

(Previously known as Emer-Seal CR)

## Highly chemical resistant, fast cure, durable, one-component joint sealant

### Uses

Sealing joints in:

- Chemical bund areas
- Floor joints in chemical processing plants
- Concrete joints exposed to acid spillage
- Swimming pools
- Sewage processing tanks
- Food, wine and citrus processing areas

### Advantages

- One component sealant - ready to use
- Fast rate of cure - reduced back to service times
- UV resistant - long life weathering resistance
- Highly resistant to biological attack such as sewers
- Highly resistant to a wide range of chemicals including strong acids and alkalis
- Highly resistant to pool chlorine, salt water chlorination and ozone treatment
- Complies to AS/NZS 4020:2005 Products in Contact with Potable Water

### Description

Nitoseal SC600 is a one part, gun applied non sag joint sealant designed for sealing expansion and construction joints exposed to aggressive chemical environments. Nitoseal SC600 utilises unique polymer technology which provides outstanding chemical resistance and cures by reaction with atmospheric moisture to form a tough flexible seal. Once cured, Nitoseal SC600 is resistant to attack from most of the aggressive chemicals used in the food, mining and chemical processing industries.

### Technical Support

Parchem offers a comprehensive range of high performance, high quality construction products. In addition, Parchem offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance.

### Design Criteria

Nitoseal SC600 may be applied to joints between 8 mm and 50 mm wide. To minimise stresses imposed on the joint sealant, all moving joints should be designed to an optimum width to depth ratio of 2:1. This ratio is subject to the following overriding minimum sealant depths:

- 8 mm minimum sealant depth on non-porous surfaces
- 12 mm minimum sealant depth on porous surfaces such as concrete and masonry
- 20 mm minimum sealant depth in applications where the sealant is subject to a hydrostatic pressure or traffic

Care must be taken to ensure joint movement does not exceed the sealant's movement accommodation capability.

If uncertain about any of the design criteria, contact your local Parchem branch for further advice.

### Properties

Data quoted is typical for this product but does not constitute a specification.

<b>Form:</b>	Non slump, thixotropic paste
<b>Hardness: - Shore A:</b>	32 ± 5
<b>Tensile modulus: 100% elongation: 100% Ultimate elongation:</b>	0.4 MPa @ 100% >1.0 MPa @ >400%
<b>Colours:</b>	Concrete Grey, Pool Blue Other colours to batch order
<b>Physical or chemical change:</b>	Chemical cure, moisture activated
<b>Application temperature:</b>	Minimum 5°C
<b>Service temperature:</b>	Minus 50°C - 150°C
<b>Tooling time:</b>	20 minutes @ 25°C 65% RH
<b>Cure rate:</b>	Approx 3 mm in 24 hours, then 1 mm / day @ 25°C / 65%RH
<b>Movement accommodation factor:</b>	± 25% butt joints (50% total)
<b>VOC content:</b>	49g / litre

# Fosroc®

## Nitoseal® SC600

### Chemical resistance - continuous immersion - (worst case testing - 6 months exposure)

\* Important: Ensure that Nitoseal SC600 is fully cured before it is subjected to chemical exposure. (Note: Service life for intermittent exposure will be significantly longer than indicated below)

Acetic Acid 10%	Resistant, > 1 month
Acetic Acid 75%	Resistant, > 1 month
Acetic Acid Conc. (Glacial)	Resistant, > 1 month
Automotive Brake Fluid	Resistant, no attack
Chlorine (Sodium Hypochlorite) 2%	Resistant, no attack
Chlorine (Sodium Hypochlorite) 10%	Resistant, no attack
Citric Acid 10%	Resistant, no attack
Diesel Fuel 100%	Intermittent spillage OK
Detergent (GN8) 2%	Resistant, no attack
Ammonium Nitrate 100%	Resistant, no attack
Ethanol 100%	Resistant, > 1 month
Heptane	Not resistant, <24 hours *
Hydrochloric Acid 10%	Resistant, > 1 month
Hydrochloric Acid 20%	Resistant, > 1 month
Hydrochloric Acid Conc. 36%	Not resistant, >2 hours *
Glycol 100%	Resistant, no attack
Lactic Acid 10%	Resistant, may discolour
Lactic Acid 25%	Resistant, may discolour
Motor Oil (unused) 100%	Resistant, no attack
Motor Oil (used) 100%	Resistant, no attack
Nitric Acid 10%	Resistant, > 1 month
Nitric Acid 25%	Resistant, > 7 days
Nitric Acid Conc. 70%	Not resistant, <1 hour *
Petrol, unleaded 100%	Not resistant, <24 hours *
Phosphoric Acid 10%	Resistant, no attack
Sodium Hydroxide 10%	Resistant, no attack
Sodium Hydroxide 25%	Resistant, no attack
Sodium Hydroxide 30%	Resistant, no attack
Sodium Hydroxide Conc. 50%	Resistant, no attack
Sugar Solution (saturated)	Resistant, no attack
Sulphuric Acid 10%	Resistant, no attack
Sulphuric Acid 25%	Resistant, no attack
Sulphuric Acid 50%	Resistant, no attack
Sulphuric Acid 75%	Resistant, > 1 month

Sulphuric Acid 98%	Not resistant, >2 hours *
Skydrol 100%	Resistant, > 1 month
Wine (Red) 100%	Resistant, no attack
Xylene	Not resistant, <24 hours *

Note: \* = suitable for intermittent exposure only.

### Specification Clauses

Where so marked on the drawings, joints are to be sealed with a high performance joint sealant offering proven performance against chemical attack. The joint sealant must be capable of accommodating +/- 25% joint movement and should be accompanied by data confirming the level of resistance of the sealant to the chemicals in question.

Joint preparation, priming and sealant application must be in strict accordance with the current technical data.

Fosroc Nitoseal SC600 supplied by Parchem is such a product.

### Applications Instructions

#### Joint preparation

Ensure that all joint dimensions are as specified, and that the anticipated joint movement is within the movement accommodation capability of Nitoseal SC600. New concrete must be allowed to cure for a minimum of 28 days before sealant installation.

Joint faces must be sound and completely dry, clean and frost free. Oil, grease, curing compounds, form release agents, and all surface contaminants must be completely removed by grinding the joint faces or by using Fosroc Solvent 10.

#### Bond breakers and joint fillers

Joints subject to hydrostatic pressure must have the sealant supported by a suitable rigid joint filler such as Fosroc Hydrocor. Joints subject to hydrostatic pressure must also contain a suitable waterstop such as a Fosroc Supercast PVC.

In joints not subject to hydrostatic pressure, a backing rod such as Expandafoam Closed Cell Backing Rod may be used. In formed joints a polyethylene bond breaker tape must be used to prevent sealant from adhering to the back face of the joint.

Note: do NOT use masking tape, electrical insulation tape or 'Gafa' tape as a bond breaker tape. Nitoseal SC600 may bond to the tapes and result in the failure of the joint sealant.

#### Priming

All joint surfaces must be sound and free from any trace of surface contamination.

Priming is not normally required on solvent cleaned glass (use only Fosroc Solvent 10 for cleaning), ceramic and metal surfaces. Where metal surfaces are treated with paints or other organic coatings, adhesion testing is recommended to ensure that adequate adhesion will be achieved.

# Fosroc®

## Nitoseal® SC600

While Nitoseal SC600 offers very good adhesion to concrete and masonry, the aggressive nature of the chemicals that may come into contact with the sealant demand that primers be used on masonry substrates. Use Fosroc Primer 13, a two part epoxy surface primer with exceptionally good hydrolytic stability which ensures good adhesion of Nitoseal SC600 to the substrate under prolonged submerged conditions. The ambient and substrate temperature needs to be above 5°C before and after the application of the primer. Mix the two components of the primer by pouring the Hardener component into the Resin component, mix thoroughly for a minimum of one minute by stirring with a spatula, paint stirrer etc. Apply an even coat of primer by brush onto the bonding faces of the concrete, the base of the joint should have no primer residue present after the primer has been applied, then allow the primer to become touch dry before applying any sealant (typically 1 hour at 23°C). **DO NOT APPLY SEALANT TO TACKY OR WET PRIMER.** The sealant must be applied within 8 hours at normal temperatures - within 3 hours at elevated temperatures (above 30°C).

The pot life (usable life) of mixed Primer 13 is 30 minutes @ 23°C and 20 minutes @ 30°C. Any unused mixed Primer 13 should be discarded after the pot life has expired.

For advice on other applications, or where Nitoseal SC600 is to be used with other substrates, contact your nearest Parchem sales office.

### Application

Fit the sausage of Nitoseal SC600 into a suitable sausage gun and gun firmly into the joint. Ensure that the sealant is forced well against all joint surfaces to achieve good surface wetting and thus optimum adhesion. Guide the nozzle along the joint gradually, applying even pressure to the trigger. The joint must be filled completely at all points.

### Tooling

Immediately after application the sealant should be tooled. Use a smooth tool to produce both the required surface finish and to assist in further forcing the sealant into good contact with the joint faces. The use of use soapy water as a tooling aid is not recommended as the cure of the sealant may be adversely affected.

### Clean up

Equipment should be cleaned promptly by wiping with Fosroc Solvent 10, as cured sealant is very difficult to remove. Cured sealant can only be removed by mechanical methods. Soaking the equipment in Fosroc Solvent 10 makes removal of cured sealant easier.

### Important notice

A Safety Data Sheet (SDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

### Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

### Limitations

Elastomeric sealants such as Nitoseal SC600 should not be applied in direct contact with bituminous materials. Nitoseal SC600 is not designed to provide resistance to organic solvents. Contact Parchem for advice if organic solvent resistance is required.

Stabilised Chlorine containing "trichloroisocyanuric acid" may cause the breakdown of surface layers of Nitoseal SC600. Also, crystallized deposits may form on the surface of the sealant from reaction of the above trichloroisocyanuric acid and urea if regular pool cleaning is not done.

Nitoseal SC600 has been tested for resistance to many chemicals including Sulphuric Acid, Hydrochloric Acid and Caustic solutions. For information regarding the resistance of Nitoseal SC600 to specific chemical solutions, contact Parchem.

### Estimating

#### Supply

Nitoseal SC600 is supplied in 600ml foil sausages.

Product	Material code
Nitoseal SC600 Concrete Grey	FC920100-600ML
Nitoseal SC600 Pool Blue	FC920101-600ML
Nitoseal SC600 White	FC920102-600ML

Primer 13 is supplied in 2 component packs.

(Base and Hardener, supplied in the correct proportions  
Complete units must be mixed to ensure correct curing)

Primer 13 (250ml pack):	Base:	FC965229-125ML
	Hardener:	FC965230-125ML
Primer 13 (1 litre pack MTO):	Base:	FC965229-500ML
	Hardener:	FC965230-500ML

**Fosroc Solvent 10:** 4 and 20 litre drums

### Coverage

Each 600 ml sausage will seal approximately 3 metres of a 20 mm x 10 mm joint.

### Storage

Nitoseal SC600 has a shelf life 24 months when stored in unopened original packaging in dry conditions, between 5°C and 30°C.