



# Renderoc TGXtra

## Shrinkage Controlled, Vertical and Overhead Cementitious Repair Mortar

### Uses

Renderoc TGXtra is suitable for hand application to repairs where light to medium load bearing is required. Typical applications would include, but not be limited to, the following:

- Vertical and overhead repairs to restore 'covercrete'.
- General concrete and masonry repairs.
- Voids greater than 10 mm deep.
- Repairs to honeycombing.
- Larger scale repairs where formwork cannot be erected.

### Advantages

Renderoc TGXtra features Dimensional Stability Technology a new materials technology; which controls the rate of drying shrinkage such that, when used correctly:

- the dimensions of the repair remain stable; and thus
- eliminating failure, due to shrinkage cracking.

This in turn leads to a series of associated benefits:

- Cost effective - shrinkage control enables repairs to be completed 'right first time'.
- Enhanced durability - works in tandem with extremely low permeability to prolong effective working life.
- Compatibility - aligns performance closer than ever before, to that of host concrete.
- User friendly - specifically developed to provide an easy to-apply product, suitable for local conditions.
- Definable performance - positive benefits are easily demonstrated via a single, simple measurement.

### Description

Renderoc TGXtra is supplied as a ready to use blend of dry powders, which requires only the addition of clean water to produce a highly consistent, lightweight repair mortar suitable for general purpose concrete and masonry repairs.

### Properties

The following results were obtained at a water : powder ratio of 0.18

Test Method	Typical Result
Drying shrinkage (ASTM C157-93)	7 days <300 microstrain 28 days <500 microstrain
Permeability (DIN 1048 Part 5)	<10 mm
Flexural Strength (BS 6319 Part 3)	> 6.5 N/mm <sup>2</sup> at 28 days
Tensile Strength (BS 6319 Part 7)	> 2.5 N/mm <sup>2</sup> at 28 days
Compressive Strength (BS 1881 Part 116 <sup>1</sup> )	>35 N/mm <sup>2</sup> at 7 days >40 N/mm <sup>2</sup> at 28 days
Water Absorption (BS 1881 Part 121)	< 2%

Note 1: 50mm cubes, air cured at 25<sup>0</sup>C

### Design Criteria

Dimensional Stability Technology is a major step forward in the general compatibility of repair mortar systems with the host concrete, and the control of shrinkage in particular.

Attention to the basic design criteria given below should ensure that the full benefits of this technology are achieved:

Recommended limits for a single application are:

Minimum applied thickness:	10 mm
Overhead sections :	up to 150 mm thick
Vertical sections :	up to 200 mm thick
Small pockets or horizontal:	up to 100 mm thick
Maximum length :	up to 3 m

# Renderoc TGXtra

Note: If the repair area exceeds 2.5 m<sup>2</sup>, consideration should be given to the use of mass fill by means of either Renderoc SPXtra spray applied mortar or Renderoc LAXtra microconcrete.

In situations where a substrate/repair barrier is required, or enhanced bond strength/working time is required, or where the substrate is likely to be damp (e.g. seawalls, quays etc.), Nitobond EP epoxy bonding agent should be used.

Water addition = 3.6 litres per 20 kg bag. Under no circumstances should part bags be used or additional water be employed. Either of these two actions will adversely affect material performance, automatically invalidating Fosroc's standard product guarantee.

## Instructions for Use

Renderoc TGXtra should be mixed and applied in strict accordance with the Product Method Statement, a copy of which may be obtained from your nearest Fosroc office.

## Estimating

### Supply

---

Renderoc TGXtra :	20 kg bags
-------------------	------------

---

### Yield

---

Renderoc TGXtra :	12.7 litres per 20 kg bag
-------------------	---------------------------

---

## Limitations

- Renderoc TGXtra should not be part mixed, nor part bags used.
- Renderoc TGXtra should not be exposed to running water either during application or prior to final set.

## Storage - Shelf life

Renderoc TGXtra has a shelf life of 12 months if kept in a dry environment, in its original packing. If stored in conditions of high temperature and/or humidity, the shelf life may be reduced to as little as 4 months.

## Standards Compliance

Renderoc TGXtra repair mortar system complies with the following international standards:

---

ASTM C157-93 :	Test for drying shrinkage
DIN 1048 Part 5 :	Test for permeability
BS 1881 Pt. 121 :	Water absorption

---

## Precautions

### Health and safety

Renderoc TGXtra contains cement powders which, when mixed with water or upon becoming damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of the dust and contact with the skin or eyes. Wear suitable protective clothing - eye protection, gloves and respiratory equipment (particularly in confined spaces).

The use of barrier creams to provide additional skin protection is also advised. In case of contact with the skin, rinse with plenty of clean water, then cleanse thoroughly with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

### Fire

Renderoc TGXtra is non-flammable and thus presents no fire hazard.

For further information, please refer to the Product Material Safety Data Sheet.



## Fosroc Sdn. Bhd.

No 8 Jalan Trompet, 33/8  
Seksyen 33, 40400 Shah Alam  
Selangor, Malaysia.

### Branch Office:

29, Jalan Zainal Abidin,  
10400 Penang, Malaysia.

[www.fosroc.com](http://www.fosroc.com)

### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

---

**telephone:**  
+60 3 5191 5660

**fax:**  
+60 3 5191 6960

**email:**  
enquiry@malaysia.fosroc.com

+60 4 2287 464

+60 4 2292 661

